

# TEST REPORT

No. **8621.SHJ1.2306.0196** Date: **07.05, 2023** Page: **1 / 8**

Applicant :

Address :

Below information submitted by the applicant:

Product Name : Squeezy sauce bottle  
Model : 1949, 150ml, PE  
Model may cover : 1956, 240ml, PE; 1957, 360ml, PE; 1966, Triple, 360ml, PE 1953,240ml,PE  
1958, 720ml, PE; 1959, 1000ml, PE; 1967, triple, 720ml, PE  
Reference info. : /  
Manufacturer info. : /  
Supplier info. :  
Buyer info. : Suprem-Inox, S.A.  
Avinguda del Progrés 93-96 Polígono Industrial Els Garrofers 08340  
Vilassar de Mar (Bcn) Spain  
Country of Destination : Spain  
Country of Origin : China

Sample Received : 06.29, 2023  
Test Period : 06.29, 2023 - 07.05, 2023  
Test Requirement : Refer to next pages  
Test Method : Refer to next pages  
Test Result : Refer to next pages  
Test Conclusion : Refer to next pages

Signed for and on behalf of  
Jordan Wang, General Manager  
BU Chemical Compliance  
TUV THURINGEN (SHANGHAI) CO., LTD.  
Location: Shanghai

## TÜV THÜRINGEN CHINA

Attention: please note that every statement made in this report is only valid for the samples tested and reported herein. This report shall not be reproduced except in full, without the written approval of the testing laboratory. Any holder of this document is advised that information contained herein reflects the parties to a transaction from exercising all their rights and obligations under the transaction documents.

[http://tuv-thuringen.com.cn/news/12\\_138](http://tuv-thuringen.com.cn/news/12_138)

VERSION: 2022.01.01

## RESULT SUMMARY

Food contact materials in accordance with General Requirement (Article 3) in EU Regulation No. 1935/2004, Commission Regulation (EU) No 10/2011 and its subsequent amendment Regulation EU No.321/2011, No.1282/2011, No.1183/2012, No.202/2014, No.865/2014, No. 2015/174, No.2016/1416, No.2017/752, No.2018/79, No.2018/213, No.2019/37, No.2020/1245 on plastic materials and articles intended to come into contact with foodstuffs, selected test items as below:

Test Items	Verdict
1. Sensory odor and taste test	PASS
2. Overall migration test; specific migration of primary aromatic amines; soluble heavy metals; specific migration of bisphenol A (BPA); specific migration of softeners and phthalates for PE plastics	PASS
3. Bisphenol A content for all polymer materials	PASS
4. PAHs content in acc. to AfPS GS 2019:01	PASS

### TESTS CARRIED BY:

LAB ID: TTSLCM001; ADD.:12F, BUILDING 1TH, NO.919, HAoyING SCI. PARK, CHONGCHUAN ZONE, NANTONG, JIANGSU, CHINA

## SAMPLE DESCRIPTION

Sample description : 1#. Semi-transparent PE materials

## TEST RESULTS

### 1. Sensorial examination odor and taste test

Test Method: sensory test with reference to DIN 10955:2023

Test Items	Test Results	Permissible Limit
	Whole product	
Test Media	Distilled water	---
Temperature, °C	40.0	---
Contact Time, hour	24.0	---
Sensorial examination odor	0.5	2.5, max
Sensorial examination taste	0.5	2.5, max
Comment(s)	PASS	---

Scale evaluation:

- 0: No perceptible odor
- 1: Odor just perceptible (still difficult to define)
- 2: Moderate odor
- 3: Moderately strong odor
- 4: Strong odor

### 2. Special requirements for plastic materials

#### 2.1. Overall migration test

Test method:

EN 1186-1:2002 guide to the selection of conditions and test methods for overall migration

EN 1186-2:2022 Materials and articles in contact with foodstuffs - Plastics - Part 2: Test methods for overall migration in vegetable oils

EN 1186-3:2022 Materials and articles in contact with foodstuffs - Plastics - Part 3: Test methods for overall migration in evaporable simulants

Test Parameter	Test Results	Permissible Limit
	1#	
Test Media	3% acetic acid	---
Temperature, °C	40.0	---

# TEST REPORT

No. 8621.SHJ1.2306.0196 Date: 07.05, 2023 Page: 3 / 8

Test Parameter	Test Results		Permissible Limit
	1#		
Contact Time, hour	24.0		---
1 <sup>st</sup> , Overall migration test, mg/dm <sup>2</sup>	<3.0		---
2 <sup>nd</sup> , Overall migration test, mg/dm <sup>2</sup>	<3.0		---
3 <sup>rd</sup> , Overall migration test, mg/dm <sup>2</sup>	<3.0		10, max
Comment(s)	PASS		---

Test Parameter	Test Results		Permissible Limit
	1#		
Test Media	Rectified olive oil		---
Temperature, °C	40.0		---
Contact Time, hour	24.0		---
1 <sup>st</sup> , Overall migration test, mg/dm <sup>2</sup>	<3.0		---
2 <sup>nd</sup> , Overall migration test, mg/dm <sup>2</sup>	<3.0		---
3 <sup>rd</sup> , Overall migration test, mg/dm <sup>2</sup>	<3.0		10, max
Comment(s)	PASS		---

## 2.2. specific migration of heavy metal

Test Method: with reference to EN 13130-1:2004, followed by analysis using ICP-OES

Test Parameter	Test Results			Permissible Limit
	1#, 1 <sup>st</sup>	1#, 2 <sup>nd</sup>	1#, 3 <sup>rd</sup>	
Test Media	3% acetic acid			---
Temperature, °C	40.0	40.0	40.0	---
Contact Time, hour	24.0	24.0	24.0	---
Soluble Aluminum, Al, mg/kg	<0.01	<0.01	<0.01	≤1.0
Soluble Ammonium, NH <sub>4</sub> , mg/kg	<0.01	<0.01	<0.01	---
Soluble Antimony, Sb, mg/kg	<0.01	<0.01	<0.01	≤0.04
Soluble Arsenic, As, mg/kg	<0.002	<0.002	<0.002	≤0.002
Soluble Barium, Ba, mg/kg	<0.10	<0.10	<0.10	≤1.0
Soluble Cadmium, Cd, mg/kg	<0.002	<0.002	<0.002	≤0.002
Soluble Calcium, Ca, mg/kg	<0.01	<0.01	<0.01	---
Soluble Chromium, Cr, mg/kg	<0.01	<0.01	<0.01	≤0.02
Soluble Cobalt, Co, mg/kg	<0.01	<0.01	<0.01	≤0.05
Soluble Copper, Cu, mg/kg	<0.10	<0.10	<0.10	≤5.0
Soluble Europium, mg/kg	<0.01	<0.01	<0.01	≤0.05
Soluble Gadolinium, mg/kg	<0.01	<0.01	<0.01	≤0.05
Soluble Iron, Fe, mg/kg	<0.50	<0.50	<0.50	≤48

# TEST REPORT

No. 8621.SHJ1.2306.0196 Date: 07.05, 2023 Page: 4 / 8

Test Parameter	Test Results			Permissible Limit
	1#, 1 <sup>st</sup>	1#, 2 <sup>nd</sup>	1#, 3 <sup>rd</sup>	
Soluble Lanthanum, mg/kg	<0.01	<0.01	<0.01	≤0.05
Soluble Lead, Pb, mg/kg	<0.01	<0.01	<0.01	≤0.02
Soluble Lithium, Li, mg/kg	<0.10	<0.10	<0.10	≤0.6
Soluble Magnesium, Mg, mg/kg	<0.01	<0.01	<0.01	---
Soluble Manganese, Mn, mg/kg	<0.10	<0.10	<0.10	≤0.6
Soluble Mercury, Hg, mg/kg	<0.002	<0.002	<0.002	≤0.002
Soluble Nickel, Ni, mg/kg	<0.01	<0.01	<0.01	≤0.02
Soluble Potassium, K, mg/kg	<0.01	<0.01	<0.01	---
Soluble Sodium, Na, mg/kg	<0.01	<0.01	<0.01	---
Soluble Terbium, mg/kg	<0.01	<0.01	<0.01	≤0.05
Soluble Zinc, Zn, mg/kg	<0.05	<0.05	<0.05	≤5.0
Comment(s)	PASS	PASS	PASS	---

### 2.3. Specific migration test of primary aromatic amine

Test method: Sample preparation with reference to EN 13130-1:2004, followed by analysis with reference to DIN 55610:1986.

Test Items	Test Results			Permissible Limit
	1#, 1 <sup>st</sup>	1#, 2 <sup>nd</sup>	1#, 3 <sup>rd</sup>	
Test Media	3% acetic acid			---
Temperature, °C	40.0	40.0	40.0	---
Contact Time, hour	24.0	24.0	24.0	---
Specific migration of 4-aminobiphenyl / 4-biphenylamine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of o-anisidine / 2-methoxyaniline, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of Benzidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4-Chloro-aniline / p-chloroaniline, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4-Chloro-o-toluidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4,4'-Diaminodiphenylether / 4,4'-oxydianiline, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4,4'-Methylenedianiline / 4,4'-diamino-diphenylmethane, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4,4-Methylenedi-o-toluidine / 3,3'-dimethyl-4,4'-diaminodiphenylmethane, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 2-Methoxy-5-methylaniline / p-cresidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4-Methoxy-mphenylenediamine/ 2,4-diaminoanisole, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of o-Toluidine / 2-aminotoluene, mg/kg	<0.002	<0.002	<0.002	≤0.002

# TEST REPORT

No. 8621.SHJ1.2306.0196 Date: 07.05, 2023 Page: 5 / 8

Test Items	Test Results			Permissible Limit
	1#, 1 <sup>st</sup>	1#, 2 <sup>nd</sup>	1#, 3 <sup>rd</sup>	
Specific migration of 2,4-Toluenediamine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 3,3-Dimethylbenzidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 2,4,5-Trimethylaniline, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of m-Phenylenediamine / 1,3-Phenylenediamine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 2-naphthylamine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of o-aminoazotoluene/ 4-amino-2',3-dimethylazobenzene/ 4-otolylazo-o-toluidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 5-nitro-o-toluidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 3,3'-dichlorobenzidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 3,3'-dimethoxybenzidine / odianisidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4,4'-methylene-bis-(2-chloroaniline) / 2,2'-dichloro-4,4'-methylene-dianiline, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4,4'-thiodianiline, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 4-amino azobenzene, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of Aniline, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 2,4-dimethylaniline/2,4-xylylidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 2,6-dimethylaniline/ 2,6-xylylidine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of m-phenylenediamine/ 1,3-phenylenediamine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of p-phenylenediamine/ 1,4-phenylenediamine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 2,6-toluenediamine, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of 1,5-diaminenaphthalene, mg/kg	<0.002	<0.002	<0.002	≤0.002
Specific migration of primary aromatic amine, mg/kg	<0.01	<0.01	<0.01	≤0.01
Comment(s)	PASS	PASS	PASS	---

## 2.4. Specific Migration of Bisphenol A

Test Method: sample preparation with reference to EN 13130-1:2004, analysis by GC/MS

Test Parameter	Test Results			Permissible Limit
	1#, 1 <sup>st</sup>	1#, 2 <sup>nd</sup>	1#, 3 <sup>rd</sup>	
Test Media	3% acetic acid			---
Temperature, °C	40.0	40.0	40.0	---
Contact Time, hour	24.0	24.0	24.0	---
Specific migration of Bisphenol A, mg/kg	<0.05	<0.05	<0.05	<0.05
Comment(s)	PASS	PASS	PASS	---

# TEST REPORT

No. 8621.SHJ1.2306.0196 Date: 07.05, 2023 Page: 6 / 8

## 2.5. Specific migration of softeners and phthalates

Test Method: Sample preparation with reference to EN 13130-1:2004, followed by analysis with GC/MS

Test Parameter	Test Results			Permissible Limit
	1#, 1 <sup>st</sup>	1#, 2 <sup>nd</sup>	1#, 3 <sup>rd</sup>	
Test Media	3% acetic acid			---
Temperature, °C	40.0	40.0	40.0	---
Contact Time, hour	24.0	24.0	24.0	---
Specific migration of DEHP, mg/kg	<0.05	<0.05	<0.05	≤1.5
Specific migration of DBP, mg/kg	<0.05	<0.05	<0.05	≤0.3
Specific migration of BBP, mg/kg	<0.05	<0.05	<0.05	≤30
Specific migration of DINP, mg/kg	<0.05	<0.05	<0.05	≤9
Specific migration of DIDP, mg/kg	<0.05	<0.05	<0.05	≤9
Specific migration of DEHT, mg/kg	<0.05	<0.05	<0.05	≤60
Specific migration of DEHA, mg/kg	<0.05	<0.05	<0.05	≤18
Specific migration of other phthalates and softeners, mg/kg	<0.05	<0.05	<0.05	≤0.05
Comment(s)	PASS	PASS	PASS	---

## 3. Bisphenol A content

Test Method: with reference to EPA 3550, solvent extracted, followed analyzed by GC/MS and LC/MS/MS


Test Parameter	Units	MDL	Test Results	Permissible Limit
			1#	
Bisphenol A content BPA, CAS No.80-05-7	mg/kg	0.05	<0.05	0.05, max

Note,

% , percentage; mg, milligrams; g, grams; kg, kilograms  
 mg/kg = milligrams per kilograms; mg/L = milligrams per litre  
 0.1% = 1000mg/kg = 1000mg/L  
 < = less than; > = greater than  
 MDL = method detection limit  
 n.d. = not detected, < MDL  
 n.a. = not applicable  
 n.r. = not required  
 EX = abbr. of Exempted

\*\*\*\*\* To be continued \*\*\*\*\*

**SAMPLE IMAGE**



*Tested sample*



*1949, 150ml, PE*



*1956, 240ml, PE*



*1957, 360ml, PE*



*1966, Triple, 360ml, PE*

# TEST REPORT

No. 8621.SHJ1.2306.0196

Date: 07.05, 2023

Page: 8 / 8



1958, 720ml, PE



1959, 1000ml, PE



1967, triple, 720ml, PE

\*\*\*\*\* END OF REPORT \*\*\*\*\*