

**Test Report**

Number: SZHH01156873

Applicant: FUJIAN DEHUA HIAP HUAT KOYO TOKI CO., LTD  
27 LONGJIN ROAD SOUTH,  
DEHUA COUNTY, FUJIAN  
CHINA

Date: May 24, 2017

Attn: WANG YUN GEN

Sample Description:

Six(6) pieces of submitted samples said to be :  
Item Name : **24 cm Round Coupe Plate HKZ080051.**  
Country of Origin : **德化.**  
Date Sample Received : May 18, 2017.



L2 9.25 "平盘 / 建白透明釉

Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued

Authorized by:  
For Intertek Testing Services Shenzhen Ltd  
Xiamen Branch



Ben N.L. Lin  
General Manager





**Test Report**

Number: SZHH01156873

Conclusion:

<u>Tested Article</u>	<u>Standard</u>	<u>Result</u>
Submitted articles	US FDA Compliancy Policy Guide Part 7117.06(2005) and 7117.07(2005) on ceramic ware	Pass
	Consent Judgment No. SF-938430 for leachable Lead and Cadmium content based on the California Proposition 65	Pass

\*\*\*\*\*

Authorized by:  
For Intertek Testing Services Shenzhen Ltd  
Xiamen Branch



Ben N.L. Lin  
General Manager





**Test Report**

Number: SZHH01156873

Tests Conducted

1 Leachable Lead (Pb) & Cadmium (Cd) Content - California

Examination of Marking on Tableware

Each submitted article was examined for the marking of the name of manufacturer/importer.

Requirement : All articles should be permanently and indelibly marked with the name of manufacturer/importer if the articles contain Lead or Cadmium.

Result :All submitted articles were not marked with the name of manufacturer/importer.

Leachable Lead (Pb) & Cadmium (Cd) Content-Internal Surface

As per US FDA CPG 7117.06(2005), 7117.07(2005) and A.O.A.C. official methods of analysis 18<sup>th</sup> edition (2005) method 973.32 by Atomic Absorption Spectrophotometric analysis.

<u>Tested Article</u>	<u>Internal Depth (mm)</u>	<u>Volume of Leaching Solution (ml)</u>	<u>Lead (ppm)</u>	<u>Cadmium (ppm)</u>
(1)	19	450	<0.05	<0.03
(2)	19	450	<0.05	<0.03
(3)	19	450	<0.05	<0.03
(4)	19	450	<0.05	<0.03
(5)	19	450	<0.05	<0.03
(6)	19	450	<0.05	<0.03
Average :			<0.05	<0.03
Limit (US FDA – Flatware) :			3.0	0.5
Limit (US California – Flatware) :			0.226	1.853

The California limit was quoted from the Consent Judgment No. SF-938430 settled by superior court of the State of California for the city and county of San Francisco, for ceramic ware - food and beverage use products (internal) based on the California Proposition 65.

ppm = parts per million = mg/L  
< = Less than

\*\*\*\*\*  
End of report

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Ltd.*